PATENT ABSTRACTS OF JAPAN

(11) Publication number:

11-322948

(43) Date of publication of application: 26.11.1999

(51) Int. CI.

C08J 3/12 // C08L101/00

(21) Application number: 10-126084

(71) Applicant: NOF CORP

(22) Date of filing:

08. 05. 1998

(72) Inventor: MARUYAMA ATSUSHI

ISHIHARA KAZUHIKO NAKABAYASHI NORIO

(54) FINE POLYMER PARTICLE AND ITS PRODUCTION

(57) Abstract:

PROBLEM TO BE SOLVED: To obtain fine polymer particles excellent in biocompatibility and safeness and useful as a drug carrier by causing a polymer obtd. by the polymn. of a monomer mixture contg. a monomer having a specific side chain to exist on the surface of a biodegradable polymer.

SOLUTION: A polymer which has a mol. wt. of pref. 1,000-1,000,000 and is obtd. by the polymn. of a monomer mixture contg. a monomer of the formula, pref. comprising the monomer and a monomer copolymerizable therewith (e.g. n-butyl methacrylate) in a molar ratio of (5:95)-(95:5), is caused to exist on the surface of a biodegradable polymer (e.g. poly-L-lactic acid) having a mol. wt. pref. of 1,000-1,000,000, thus giving the objective polymer particles. In the formula, R1 to R3 are each H or a 1-4C alkyl; and (n) is 1-4. Pref., the resultant fine polymer particles are spherical

$$-0 - \frac{1}{p} - 0 - 10 \, \mathrm{H}_{2^{3} - n} - N^{4} \left(-\frac{R^{3}}{R^{3}} \right)$$

resultant fine polymer particles are spherical and have particle sizes of 1-100,000 nm.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's

decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted

registration]

[Date of final disposal for application]

[Patent number]

Best Available Copy

[Date of registration]
[Number of appeal against examiner's decision of rejection]
[Date of requesting appeal against examiner's decision of rejection]
[Date of extinction of right]

Copyright (C); 1998, 2003 Japan Patent Office

Best Available Copy